



BETA UHS 2K CLEARCOAT

ULTRA HIGH SOLID 2K CLEARCOAT

Clearcoat compatible with waterborn paint systems. High quality clearcoat for top quality clear on metallic base finishes. BETA UHS CLEARCOAT is characterised by extremely good flow and depth of gloss. It also protects against weathering and environmental pollution. BETA UHS CLEARCOAT can be used with special effect paints (such as pearl effect, crystal effect and brilliant effect). Thanks to its ultra high solid contents and ease of application, BETA UHS CLEARCOAT guarantees top results, economy of product and time.

Mixing ratio: 2 ÷ 1

BETA UHS CLEARCOAT	100 CC
BETA 2000 UHS HARDENER	50 CC
BETA CRIL THINNER 2K	5 - 10%

Pot life: 2 hours at 20°C
15 - 16 sec CF4 at 20°C

Nozzle:

Gravity feed: Ø 1,3 - 1,4 mm
Suction feed: Ø 1,6 mm
H.V.L.P.: Ø 1,2-1,3 mm
Spray pressure: 3 - 3 ,5 atm / bar

2 coats. The second one 10 min after the first one

Flash off time: 5 - 10 min at 20°C

Baking: 40 min at 50° - 60°C
Air drying: 8/12h at 20°C

Polishing and sanding 24 h after

PACKING:

9 CANS OF 1L
4 CANS OF 5L